



## PRODUCT DATA SHEET

**NORGLASS LABORATORIES PTY.LTD.**  
A.B.N. 92 001 807 245  
P.O. Box 312, Neutral Bay. NSW 2089 Australia  
59 Moxon Road, Punchbowl NSW  
Ph: 61 2 9708 2200 Fax: 61 2 9796 3069  
Email: norglass@bigpond.net.au  
www.norglass.com.au



## NORGLASS PAVING PAINT (SLIP RESISTANT & SMOOTH)

**DESCRIPTION:** A fast drying, low-odour, low-sheen finish with plastic granules incorporated into the coating for positive traction when wet. Can be applied to clean, dry, bare fibro, concrete, or timber without priming. Easily recoated.

### PROPERTIES (at 20°C)

**COLOURS:** Clay, Terracotta, Slate, Russet, Lincoln Green, Pewter, Sand, Ironbark and Ivory. Can be tinted with domestic tinters for a wide range of pastel shades. Colours can also be intermixed with each other or Ivory to reduce intensity.

**TOXICITY:** N/A

**FINISH:** Low-sheen.

**COVERAGE:** 7-8 square metres/litre on untreated smooth surfaces; 8 - 9 square metres/litre on sealed smooth areas. On rough surfaces allow more paint.

**DRYING TIME:** Touch dry in 2 hours.

**RECOATING:** Recoatable after 4 hours 25°C. Light traffic after 8 hours and 24 hours for normal use

**POT LIFE:** N/A

**MIXING RATIO:** N/A

**THINNING:** Not normally recommended, but up to 3% of Weatherfast Brushing Thinner can be added in hot weather. (i.e. 30mls per litre)

**WEIGHT/LITRE:** 1.22kg.

**FLASH POINT:** 32 °C.

**CLEAN UP:** Weatherfast Brushing Thinner or Weatherfast Spraying Thinners

**UN NUMBER:** 1263

- PREPARATION:** Scrub down previously painted surfaces with a commercial cream cleaning agent, using hot water. Hose off thoroughly with fresh water and allow to dry. Sand off any unsound or flaking paint before proceeding. Unpainted concrete must be washed with bleach, liquid pool chlorine or other proprietary concrete cleaner, hosed off and allowed to thoroughly dry before painting.
- APPLICATION:** Normally by brush and short nap Roller. However spraying can be done using HVLP spray equipment where conditions are suitable. Thin sparingly with Weatherfast Spraying Thinners. When rolling it is advisable to use the roller in one direction only to obtain a uniform deposition of granules. Work systematically to maintain a wet edge (where possible)  
**NOTE:** Where the gradient is steep it may be advisable to contact NORGLASS TECHNICAL ADVISORY SERVICE before applying.
- TRANSPORTATION:** Flammable liquid.  
Dangerous Goods Class 3.2  
Sizes available: 20litre, 10litre, 4litre, 1litre
- PRECAUTIONS:** Provide adequate ventilation during use.  
Do not smoke and keep away from naked flames.  
On very dry concrete surfaces a third coat may be required to produce an even result due to absorption.  
Do not use on areas of constant immersion.
- FIRST AID:** If skin contact occurs – wash with soap and water.  
If eye contact occurs – irrigate with plenty of fresh water.  
If inhaled – remove to fresh air and rest.  
If swallowed – DO NOT induce vomiting. Give water or milk and seek Medical advice or contact the Poisons Information Centre on 131 126.
- SPECIAL** Do not use below 10°C as drying will be inhibited and moisture entrapment will likely impair the finish.
- INSTRUCTIONS:** **NOTE:** Thorough stirring is essential before use due to the weight of the plastic granules (they tend to float) and have to be dispersed into the film before applying.